



## Oil & Gas - Cable Solutions

# Exploration & Production

## ESP Cables

### Round Cables

## DEVILENE R 285 °F

Round cable providing a high degree of flexibility and crush resistance. For easier installation and maintenance, Prysmian ESP cables are shipped on reels of a continuous, splice-free length. Maximum permissible temperature is 285 °F (140 °C).

### APPLICATION

Downhole extraction systems are critical for crude oil extraction. The reliability of the electrical power supply to an Electrical Submersible Pump (ESP) system depends on the performance and reliability of the power feed through to the wellhead, power cable, motor lead cable, pig tail connectors and related equipment such as the pump and motor. Prysmian ESP cables offer an efficient, rugged and easy to handle solution that delivers reliable performance in a package that is straightforward to install and maintain.

### STANDARDS & APPROVALS

IEEE 1018.

### QUALITY & TESTING

Prysmian has a built-in multi-step quality assurance program, covering the production process from cable design and raw material purchases to final inspection and testing documentation.

The ISO 9001 quality system of Prysmian Group (together with ISO 14001 and OHSAS 18001) has been assessed, approved and is currently audited by SGS.

### DESIGN & CONSTRUCTION

#### 1 CONDUCTOR

Solid or stranded plain (or tinned) copper conductors. A special sealing compound completely fills the interstitial spaces between the strands to prevent gas migration.

#### 2 INSULATION

A proprietary high quality EPDM compound is chemically bonded to the conductor. It is specially formulated to provide high dielectric and low swell characteristics in presence of oil.

#### 3 TAPE

A fluoropolymer tape is helically applied over the insulation to provide added protection against oil and insulation decompression.

#### 4 BRAID


A synthetic braid, applied with full coverage over the fluoropolymer tape, provides additional mechanical reinforcement and hoop strength.

#### 5 JACKET

A proprietary Nitrile rubber (NBR) formulation, specially compounded to provide excellent heat, oil resistance and low swell, is extruded over the cabled insulated conductors.

#### 6 ARMOUR

An interlocking, fully galvanized (4-sides) steel tape armour provides excellent mechanical protection with a high degree of flexibility and enhanced crush resistance, available in thickness of 0.025" or 0.034". Stainless steel or Monel 400 armour is available for use in highly corrosive well environments. A selection of various armour profiles is available to suit various downhole applications.







## Oil & Gas - Cable Solutions

### Exploration & Production

## ESP Cables

### Round Cables

#### PERFORMANCES / RATINGS

CHEMICAL RESISTANCE	MAXIMUM AXIAL LOAD	MIN. INSTALLATION TEMPERATURE	MAX. RATED TEMPERATURE	MIN. BENDING RADIUS FOR INSTALLED CABLES
 galvanised steel tape: good stainless steel tape: very good monel tape: excellent	 50 N/mm <sup>2</sup>	 -22 °F (-30 °C)	 +284 °F (+140°C)	 7 times overall diameter

#### TECHNICAL DATA

##### DEVILINE R 285 °F - 3 Conductors EPDM/NBR/GSTA 5 kV - Insulation thickness 0,075" (1,91 mm)

SIZE		CONDUCTOR STRANDS	CONDUCTOR DIAMETER		INSULATION THICKNESS		INSULATION DIAMETER		DIMENSIONS UNDER ARMOUR		OVERALL DIMENSIONS		WEIGHT		ELECTRICAL PARAMETERS	
(awg)	(mm <sup>2</sup> )	(nr)	(in)	(mm)	(in)	(mm)	(in)	(mm)	(in)	(mm)	(in)	(mm)	(lb/kft)	(kg/km)	(Ω/kft)	(Ω/kft)
1	42,4	7	0,331	8,41	0,075	1,91	0,49	12,4	1,24	31,5	1,44	36,6	1850	2750	0,193	0,034
1	42,4	1	0,289	7,34	0,075	1,91	0,44	11,2	1,15	29,2	1,35	34,3	1725	2565	0,188	0,033
2	33,6	7	0,292	7,42	0,075	1,91	0,45	11,4	1,15	29,2	1,35	34,3	1595	2375	0,251	0,035
2	33,6	1	0,258	6,55	0,075	1,91	0,41	10,4	1,08	27,4	1,28	32,5	1500	2230	0,244	0,035
4	21,2	1	0,204	5,18	0,075	1,91	0,36	9,1	0,96	24,4	1,16	29,5	1150	1710	0,377	0,037
6	13,3	1	0,162	4,11	0,075	1,91	0,32	8,1	0,87	22,1	1,07	27,2	920	1370	0,597	0,040

##### DEVILINE R 285 °F - 3 Conductors EPDM/NBR/GSTA 5 kV - Insulation thickness 0,090" (2,29 mm)

SIZE		CONDUCTOR STRANDS	CONDUCTOR DIAMETER		INSULATION THICKNESS		INSULATION DIAMETER		DIMENSIONS UNDER ARMOUR		OVERALL DIMENSIONS		WEIGHT		ELECTRICAL PARAMETERS	
(awg)	(mm <sup>2</sup> )	(nr)	(in)	(mm)	(in)	(mm)	(in)	(mm)	(in)	(mm)	(in)	(mm)	(lb/kft)	(kg/km)	(Ω/kft)	(Ω/kft)
1	42,4	7	0,331	8,41	0,090	2,29	0,52	13,2	1,30	33,0	1,50	38,1	1945	2895	0,193	0,035
1	42,4	1	0,289	7,34	0,090	2,29	0,47	11,9	1,21	30,7	1,41	35,8	1815	2700	0,188	0,035
2	33,6	7	0,292	7,42	0,090	2,29	0,48	12,2	1,22	31,0	1,42	36,1	1685	2510	0,251	0,036
2	33,6	1	0,258	6,55	0,090	2,29	0,44	11,2	1,14	29,0	1,34	34,0	1585	2360	0,244	0,036
4	21,2	1	0,204	5,18	0,090	2,29	0,39	9,9	1,03	26,2	1,23	31,2	1230	1830	0,377	0,039
6	13,3	1	0,162	4,11	0,090	2,29	0,35	8,9	0,94	23,9	1,14	29,0	1000	1485	0,597	0,042

r = conductor electrical resistance at 285 °F | x= inductive reactance at 60 Hz

Note: overall dimensions and weights are based on 0.025" armour tape thickness

This product information sheet is provided for reference only.

For Voltage Drop/Ampacity data, please contact your Prysmian representative.

#### CONTACT INFO:

prysmianoilandgas@prysmiangroup.com  
[www.prysmiangroup.com/contact-us](http://www.prysmiangroup.com/contact-us)

**Prysmian**  
Group